

Valox* Resin K4530

Americas: COMMERCIAL

15% glass reinforced PBT, Hydrolytically stable, High flow, Automotive connectors.

Property

TYPICAL PROPERTIES ⁽¹⁾			
	Value	Unit	Standard
MECHANICAL			
Tensile Stress, yld, Type I, 5 mm/min	103	MPa	ASTM D 638
Tensile Stress, brk, Type I, 5 mm/min	103	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Tensile Modulus, 5 mm/min	3550	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	150	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4640	MPa	ASTM D 790
IMPACT			
Izod Impact, unnotched, 23°C	400	J/m	ASTM D 4812
Izod Impact, notched, 23°C	58	J/m	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	218	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	193	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.41	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.7 - 0.9	%	SABIC Method
Mold Shrinkage, xflow, 3.2 mm	1 - 1.2	%	SABIC Method
AFTER 40 CYCLES, SIMILAR TO USCAR-2, CLASS III			
Tensile Stress, brk, Type I, 5 mm/min	82	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	4520	MPa	ASTM D 790
Flexural Strain, 1.3 mm/min, 50 mm span	9.7	%	ASTM D 790
Instrumented Impact, Total Energy, 23°C	6	J	ASTM D 3763
PROPERTIES AFTER 1008 HOURS AT 125°C			
Tensile Stress, brk, Type I, 5 mm/min	98	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	4	%	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	4820	MPa	ASTM D 790
Flexural Strain, 1.3 mm/min, 50 mm span	7	%	ASTM D 790
Instrumented Impact, Total Energy, 23°C	5	J	ASTM D 3763
AFTER 40 CYCLES, SIMILAR TO USCAR-2, CLASS IV			
Tensile Stress, brk, Type I, 5 mm/min	89	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.3	%	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	5100	MPa	ASTM D 790
Flexural Strain, 1.3 mm/min, 50 mm span	6	%	ASTM D 790
Instrumented Impact, Total Energy, 23°C	4	J	ASTM D 3763
PROPERTIES AFTER 1008 HOURS AT 155°C			
Tensile Stress, brk, Type I, 5 mm/min	4812	MPa	ASTM D 638
Tensile Strain, yld, Type I, 5 mm/min	97.2	%	ASTM D 638
Flexural Modulus, 1.3 mm/min, 50 mm span	0	MPa	ASTM D 790

Flexural Strain, 1.3 mm/min, 50 mm span	3.8	%	ASTM D 790
---	-----	---	------------

Source GMD, last updated:03/25/2004

Processing

- We cannot overemphasize -- OVERDRYING SHOULD BE AVOIDED. Use a dehumidifying desiccant bed dryer with -30°C (-20°F) dew point air (approximately 1 cfm/lb/hr air flow). Exceeding the temperature or time recommended can compromise the hydrolysis performance of the material or the drying equipment can be damaged.

Parameter	Value	Unit
Injection Molding		
Drying Temperature	60 - 75	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.05	%
Melt Temperature	250 - 265	°C
Nozzle Temperature	245 - 260	°C
Front - Zone 3 Temperature	250 - 265	°C
Middle - Zone 2 Temperature	245 - 260	°C
Rear - Zone 1 Temperature	240 - 255	°C
Mold Temperature	65 - 90	°C
Back Pressure	0.3 - 0.7	MPa
Screw Speed	50 - 80	rpm
Shot to Cylinder Size	40 - 80	%
Vent Depth	0.025 - 0.038	mm

Source GMD, last updated:03/25/2004

- If material is stored in dryer for extended periods (overnight or more):
 - Lower dryer temperature to room temperature.
 - Recirculate cool dry air over material.

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

- (1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design,

or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Valox is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company. All rights reserved